

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C08G 18/28, D01F 6/70</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/11688</b> <b>(43) International Publication Date:</b> 11 March 1999 (11.03.99)
<b>(21) International Application Number:</b> PCT/US98/18428 <b>(22) International Filing Date:</b> 3 September 1998 (03.09.98)  <b>(30) Priority Data:</b> 9/256144 3 September 1997 (03.09.97) JP  <b>(71) Applicants (for all designated States except US):</b> E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). DU PONT-TORAY COMPANY, LTD. [JP/JP]; 5-6, Nihon-bashi Honcho 1-chome, Chuo-ku, Tokyo 103 (JP).  <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only):</b> UMEZAWA, Masao [JP/JP]; 171-32, Kobirai, Rittocho, Kuritagun, Shiga 520-30 (JP).  <b>(74) Agent:</b> FRANK, George, A.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		<b>(81) Designated States:</b> US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> SPANDEX PRODUCTION METHOD AND THE SPANDEX SO MADE  <b>(57) Abstract</b>  A process for melt-spinning solution-polymerized polyurethanes, based on polyether glycols and MDI at an addition ratio of 1.8 to 6.0, glycol chain extenders and a chain terminator to produce number average molecular weights of the polyurethanes of 40,000-150,000, and 5-2500 decitex spandex made thereby, are provided.		

BEST AVAILABLE COPY

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE

## SPANDEX PRODUCTION METHOD AND THE SPANDEX SO MADE

BACKGROUND OF THE INVENTION5 Field of the Invention

The present invention concerns a method of melt-spinning polyurethanes into textile decitex spandex and, more particularly, a method using ethylene glycol chain extender in the preparation of the polyurethane.

10

Discussion of Background Art

Spandex based on polymeric glycols, diisocyanates, and aliphatic diols is known. Ethylene glycol has been disclosed as a chain extender for making thermoplastic polyurethane-based spandex, but its use in making melt-spun spandex leads to the difficulty in melt-spinning such polyurethanes. U.S. Patent 3,649,600 discloses spandex based on poly(tetramethyleneether) glycol 1,1'-methylenebis(4-isocyanatobenzene) and 1,4-butane-  
15 diol, polymerized in a two-step melt-polymerization process in the presence of 0.06-0.3% by weight of water based on the polymeric glycol. Although fibers are prepared, the high softening point of the polyurethanes obtained is expected to give poor spinnability due to  
20 excessive cross-linking at the high temperature needed to melt-spin the polymers.

Japanese Published Patent Application 04-146915 and United States Patent 5,391,682 disclose a two-step melt polymerization and melt spinning of high molecular  
30 weight, number average above 160,000, polyurethanes under special conditions of high shear and a total glycol to isocyanate ratio range of 0.95 to 1.05. The product polyurethane is said to contain up to 500 crystalline particles (clumps) per kilogram.

35 Japanese Published Patent Application 05-214062 discloses melt polymerization and melt spinning of 2G-extended polyurethanes under special conditions of high

shear rates (at least  $10,000 \text{ sec}^{-1}$ ) and very short residence times (60-300 seconds), without providing any examples using 2G, which can be used for pelletizing the large diameter strands. There is no disclosure of small-diameter textile fibers, whose manufacture makes more stringent demands on polymer quality.

There remains a need to be able to prepare polyurethanes based on ethylene glycol chain extender which can be reliably melt-spun into textile decitex fibers having useful properties.

#### SUMMARY OF THE INVENTION

The process of this invention for preparing melt-spun spandex comprises the steps of:

- a) contacting in a solvent
  - i) a polymeric glycol selected from the group consisting of poly(tetramethyleneether) glycol and poly(tetramethyleneether-co-3-methyltetramethylene-ether) glycol having a number average molecular weight of 2400-8000,
  - ii) 1,1'-methylenebis(4-isocyanatobenzene) at a molar addition ratio of polymeric glycol to isocyanate of 1.8-6.0:1 and
  - iii) a chain extender selected from the group consisting of ethylene glycol, 1,3-propanediol, and 1,4-butanediol, to form a polyurethane;
- b) adding a monofunctional chain terminator in order to obtain a polyurethane having a number average molecular weight 40,000-150,000 and a softening point of not more than  $230^{\circ}\text{C}$ ;
- c) removing the solvent; and
- d) melt-spinning the polyurethane to form spandex.

#### DETAILED DESCRIPTION OF THE INVENTION

As used herein, the term "spandex" has its customary meaning, that is, a manufactured fiber in which the fiber-forming substance is a long chain synthetic elastomer comprised of at least 85% by weight

of a segmented polyurethane. The segments in the polyurethane are classified into "soft" segments of polyether-urethane blocks and "hard" segments containing aromatic and urethane groups.

5        Suitable polymeric glycols include poly(1,4-tetramethyleneether glycol) (PO4G) and copolymers of tetrahydrofuran and 3-methyltetrahydrofuran (3MePO4G) having a number-average molecular weight of about 2400-8000. 3MePO4G having 4-20 mole percent 3-methyl  
10        moieties and a molecular weight of about 2400-4500 is preferred. When the molecular weight of polymeric glycol is less than 2400, the recovery properties of the resulting yarn tend to become low and it becomes difficult to obtain the desired elongation. When the  
15        molecular weight of the polymeric glycol exceeds 8000, the strength decreases and the resistance to chemicals declines. Use of the preferred 3MePO4G glycol gives spandex having a particularly good balance of mechanical properties.

20        The diisocyanate used in the process of this invention is 1,1'-methylenebis(4-isocyanatobenzene) (MDI). Other diisocyanates can be included in minor amounts, provided they do not compromise the advantageous effects of the invention.

25        The chain extender used in the method of the present invention is selected from the group consisting of ethylene glycol (abbreviated hereinafter as 2G), 1,3-propanediol (3G) and 1,4-butanediol (4G). 2G is preferred and presents the most demands on stable melt-  
30        spinning of polyurethanes prepared with it. This is because polyurethanes made with 2G have a high hard segment melting point (about 240°C). The hard ratio (the molar ratio of 2G to polymeric glycol) is in the range of about 1.75 to 3.0. Other diol chain extenders  
35        can be included in minor amounts.

A monofunctional chain terminator is used in the process of the present invention to control the molecular weight of the polyurethane. For

polyurethanes useful in melt-spinning spandex, this number average molecular weight is determined to be 40,000-150,000. Useful chain terminators include monoamines, monoalcohols and monoisocyanates.

5 Aliphatic alcohols are preferred, and n-butanol is especially preferred. The chain terminator can be added at the beginning or the end of the polymerization. Addition at the end of the polymerization is preferred for more uniform molecular  
10 weight distribution.

Any suitable solvent can be used in the polymerization process of the present invention, such as dimethylacetamide ("DMAc"), dimethylformamide, dimethylsulfoxide, n-methylpyrrolidone, and mixtures  
15 thereof.

The ingredients for the solution polymerization can be added in one step or in two steps. In the one-step method, the polymeric glycol, MDI and diol chain extender are added substantially simultaneously. In  
20 the two-step method, the polymeric glycol and MDI are first mixed to allow the formation of an isocyanate-terminated prepolymer, after which the diol chain extender is added to form a polyurethane. The one-step method is preferred because of its simplicity and low  
25 cost. In the one-step method, good results can be obtained when the starting materials are added to the solution at a relatively low temperature (for example in the range of about 20°C-30°C), the temperature is raised to the reaction temperature (for example at  
30 least about 70°C) and, once a preselected degree of polymerization has been reached, the chain terminator is added.

After the completion of the above steps, any suitable method can be used to remove the solvent from  
35 the polymer solution. Typically the solvent can be removed in a vacuum or with hot air, and, alternatively, the solution can be poured into steam or water. A devolatilizing extruder, such as that used in



Canadian Patent 1,321,852, can also be used so that polyurethanes can be continuously polymerized and spun. Methods combining these approaches can also be used.

Polyurethane from which the solvent has been removed in this way can be generally processed into chips, flakes, particles and the like. Chips offer the advantage of being easy to transport, in addition to which any further required drying is easy. Because the resulting polyurethane is sometimes tacky, the addition of a suitable lubricant or antitack agent such as silicone oil, calcium stearate, sodium stearate, magnesium stearate, talc, barium sulfate, and the like can be useful. These lubricants and antitack agents can be added to the solution or during the course of solvent removal.

The polyurethane which has been desolvated in this way is optionally further dried as needed. Any conventional drying method can be employed without particular limitation as to either the drying conditions or the method. Particularly advantageous methods include vacuum drying and drying in heated dry nitrogen.

The solution polymerization process of the invention requires a molar ratio of diisocyanate to polymeric glycol (the "addition ratio") of about 1.8-6. The resulting polyurethane has a softening point of not more than about 230°C (preferably not more than 220°C) and a number average molecular weight of about 40,000-150,000. When the addition ratio is less than about 1.8, the melting point of the spandex is unsatisfactorily low, and when it exceeds about 6, the elongation of the spandex decreases too much and the hand of the spandex becomes hard. An addition ratio in the range of about 2.5-3.7 is preferred for improved properties such as high softening point, high recovery, and good heat settability. When the softening point exceeds 230°C, melt spinning becomes difficult to carry out and heat-settability decreases. When the number-average molecular weight is less than about 40,000, the

strength and elongation tend to be low and the yarn becomes fragile. When the molecular weight is greater than about 150,000, the elongation becomes low, and filter clogging can occur during melt-spinning.

5       The polyurethane that has been thus prepared is then melt-spun to form spandex. Any conventional melt spinning method can be employed.

10       The cross-section of the spandex of the present invention can be circular, flattened, or of any other suitable cross-section. The fiber decitex can be in the range of about 5-2500 dtex and preferably in the range of about 10-135 dtex. The spandex of this invention can comprise a single filament or two or more united filaments.

15       Various stabilizers, pigments and the like can be added to the polyurethane, even in the spinning step. Useful additives include light stabilizers and antioxidants such as hindered phenols, including 2,6-di-t-butyl-4-methylphenol and Sumilizer GA-80  
20       (manufactured by Sumitomo Chemical Co., Ltd., Tokyo, Japan), benzotriazoles (e.g., various Tinuvins, made by Ciba Specialties), phosphorus-based chemicals (e.g., Sumilizer P-16, manufactured by Sumitomo), and amine-type chemicals (various Tinuvins); inorganic pigments  
25       such as titanium oxide, zinc oxide and carbon black; clay minerals such as montmorillonite; metallic soaps such as magnesium stearate; microbicides and deodorants such as silver, zinc and compounds thereof; lubricants such as silicones and mineral oils; and various  
30       antistatic agents such as barium sulfate, cerium oxide, betaine and phosphoric acid compounds. These additives can be added during the spinning step or in the polymerization step.

35       It is preferred that the fiber thus obtained be constant-length or relaxation heat-treated in an additional step in order to increase its elongation-at-break. It is more preferred that heat treatment be performed on relaxed fiber, during which the relaxation ratio (the ratio of feed roll rpm to takeup roll rpm



during heat treatment) is not more than about 40%.

Heat treatment can be carried out by treatment with dry heat or wet heat, for example by steam or an infrared heater. The heat-treatment temperature can vary

5 according to the treatment medium, but is generally in the range from about 70°C up to about 5°C below the polyurethane softening point. When dry heat is used, the temperature is in the range from about 90°C to about 10°C below the polyurethane softening point.

10 Such heat treatment can be carried out in the spinning step or in a later step and can be carried out in one step or in multiple steps.

The number-average molecular weight of the polyurethanes made by the method this invention was  
15 measured by gel permeation chromatography (GPC), using a polystyrene standard. "Softening point," as used herein, refers to the value measured by thermal mechanical analysis (TMA) of a dry film obtained by casting the polyurethane solution of the invention into  
20 a film which is then dried at 120°C. Polymer solution viscosity was determined in accordance with the general method of ASTM D1343-69 with a Model DV-8 Falling Ball Viscometer, (made by Duratech Corp., Waynesboro, VA.), operated at 40°C.

25 Mechanical properties of the spandex were measured by using an Instron 4502 tensile tester. Five-cm long fiber samples were extended to 300% elongation at a rate of 50 cm/min and allowed to relax. This cycle was repeated five times, and then the sample were held at  
30 300% elongation for 30 seconds.

"Stress relaxation ratio" was the percent reduction in stress after holding the sample at the final extended length for 30 seconds following the fifth 300% extension. The sample was subsequently  
35 allowed to fully relax from the extension.

The ratio of the sample length when the stress became zero following relaxation from extension to the length before extension was the "set ratio". Tenacity at break and elongation at break were, respectively,

the elongation and stress when, in the above measurement procedure, the fiber was extended a sixth time until it broke.

5 The hysteresis ratio was the stress, measured at 200% extension on the stretch part of the fifth 0-300% stretch-and-relax cycle, divided by the stress at 200% extension on the relax part of the fifth cycle after the extended length had been held for 30 seconds and then released.

10 To determine the heat-setting percent, the fiber was treated in a free, unsecured state for 10 minutes with 100°C steam, then treated in an unsecured state for 2 hours with boiling water, and then dried at room temperature for one day. The fiber was then extended  
15 100%, treated with 115°C steam for 1 minute, and subsequently treated with 130°C air for 1 minute at the same degree of extension. Next, the fiber was left to stand at room temperature for one day, and the final length was measured. The heat setting percent was  
20 calculated as the final length divided by the length at 100% extension, multiplied by 100.

#### EXAMPLE 1

PO4G, number average molecular weight 3,000 (10  
25 kg), MDI (2.65 kg) and 2G (0.44 kg) were added substantially simultaneously to 20 kg of DMAC with stirring. The temperature of the resulting solution was then raised to 70°C, and the heated solution was stirred with a mechanical paddle stirrer for 7 hours,  
30 followed by the addition of 66 grams of n-butanol. The solids content of the solution was 40wt%. The addition ratio for this polyurethane was 3.18, the hard ratio was 2.13, and the number-average molecular weight was determined to be 80,000. When melt spun, the resulting  
35 fiber had good tenacity at break. The softening point of this polyurethane was about 200°C.

Next, stabilizing additives were incorporated into the polymer solution by conventional slurry addition

and mixing so that the polyurethane fiber contained 2.0 wt% Methacrol® 2462B (a polymer of bis(4-isocyanato-cyclohexyl)methane and 3-t-butyl-3-aza-1,5-pentane-diol), 1.2 wt% Methacrol® 2390D (a condensation  
5 polymer of p-cresol and divinyl benzene), both products of E.I. du Pont de Nemours and Company, and a small amount of silicone oil. The viscosity of this polymer solution was 3,800 poise at 40°C.

This solution was extruded as strand onto a net  
10 conveyor, and the strand was sprayed with 120°C steam and then with water, passed through a cutter, and rendered into chips which were then vacuum dried at 80°C. The chips were melted in a single-screw extruder, then metered with a gear pump and melt-spun  
15 through a spinneret into a spinning chimney through which a stream of cooling air was being passed. The speed ratio between the godet (feed) roller and the windup unit was 1.40, and the melt-spinning was carried out at 350 m/min. The resulting 13 decitex  
20 monofilament fiber was wound onto conventional cardboard tubes. The spinnability was good and free of any problems. The properties of this yarn are shown in the Table. Yarn having a high tenacity at break and a relatively high hysteresis ratio was obtained.

25

#### EXAMPLE 2

Poly(tetramethyleneether-co-3-methyltetra-  
methyleneether) glycol, number average molecular weight 3,500 and a 3-methyltetramethylene-ether moiety content  
30 of 12.5 mole percent (10.5kg), MDI (2.52 kg) and 2G (0.41 kg) were added substantially simultaneously to 20 kg of DMAC with stirring. The resulting solution was then raised to a temperature of 70°C and reacted in the same way as in Example 1, followed by the addition of  
35 0.2 wt% (based on total solution weight) of n-butanol. The solids content of the solution was 40%. The addition ratio for this polyurethane was calculated to be 3.3, and the hard ratio 2.20. The softening point

of this polyurethane was about 200°C. The number average molecular weight was determined to be 70,000. When melt-spun, the resulting fiber had good tenacity at break. Next, an additive package was added as in  
5 Example 1, giving a solution whose viscosity was 4,100 poise at 40°C. This solution was then rendered into chips by the same method used in Example 1, which were also melt-spun as in Example 1. The speed ratio between the godet roller and the windup unit was 1.25,  
10 and melt-spinning was carried out at 450 m/min. The resulting 13 decitex monofilament fiber was wound onto conventional cardboard tubes. The spinnability was good and free of any problems.

The properties of this yarn are also shown in the  
15 Table. Yarn having good recovery properties (such as low set and stress relaxation ratios), high elongation at break, and low hysteresis ratio was obtained.

### EXAMPLE 3

20 The yarn prepared in Example 2 above was fed by a feed roll through a 130°C hollow (tunnel) heater, passed around a takeup roll at a relaxation ratio of 20%, and wound up. The residence time of the yarn in the heater was about one second. The properties of  
25 this yarn are also shown in the Table and show that an even higher elongation at break was obtained.

Table 1

	Ex. 1	Ex. 2	Ex. 3
Softening point (°C)	200	200	200
Elongation at break (%)	350	410	480
Tenacity at break (dN/tex)	1.3	0.8	0.6
Set Ratio	1.26	1.20	1.23
Stress relaxation ratio (%)	33	24	27
Heat setting (%)	60	66	58
Hysteresis ratio	4.5	1.4	1.7

COMPARATIVE EXAMPLE 1

Using the same ratios of PO4G, MDI and 2G as in Example 1 but without the addition of the chain terminator n-butanol, melt polymerization was carried out in a twin screw extruder (model no. S2-5KRCVP kneader), made by Kurimoto Steel Company, Japan) at about 180°C, a shear rate of about 1000 sec<sup>-1</sup> and about 5 seconds residence time. The polymer melt was cloudy and discolored. Chips could not easily be made for melt-spinning, but a small amount of polymer grains was made by hand-cutting. During attempted melt-spinning these grains, the fiber curled and twisted just below the spinneret, and the fiber frequently broke during spinning.

15

COMPARATIVE EXAMPLE 2

Using the ratios of 3MePO4G, MDI and 2G as in Example 2 and, again, without the addition of n-butanol, polymerization was carried out as in Comparative Example 1, with the same results.

20

Claims:

1. A process for preparing melt-spun spandex comprising the steps of:
  - a) contacting in a solvent
    - 5 i) a polymeric glycol selected from the group consisting of poly(tetramethyleneether) glycol and poly(tetramethyleneether-co-3-methyltetramethylene-ether) glycol having a number average molecular weight of 2400-8000,
    - 10 ii) 1,1'-methylenebis(4-isocyanatobenzene) at a molar addition ratio of polymeric glycol to isocyanate of 1.8-6.0:1 and
    - iii) a chain extender selected from the group consisting of ethylene glycol, 1,3-propanediol, and  
15 1,4-butanediol, to form a polyurethane;
  - b) adding a monofunctional chain terminator in order to obtain a polyurethane having a number average molecular weight 40,000-150,000 and a softening point of not more than 230°C;
  - 20 c) removing the solvent; and
  - d) melt-spinning the polyurethane to form spandex.
2. The process of claim 1 wherein the chain  
25 extender is ethylene glycol, the chain terminator is an aliphatic alcohol, and the softening point is not more than 220°C.
3. The process of claim 2 wherein the  
30 polyurethane is formed in two steps by contacting the polymeric glycol with 1,1'-methylenebis(4-isocyanatobenzene) to form an isocyanate-terminated prepolymer and then contacting the prepolymer with the ethylene glycol.
- 35 4. The process of claim 2 wherein the polyurethane is formed in one step by adding the polymeric glycol, 1,1'-methylenebis(4-isocyanato-



benzene) and ethylene glycol substantially simultaneously.

5        5. The process of claim 4 wherein the polymeric glycol, 1,1'-methylenebis(4-isocyanato-benzene), and ethylene glycol are mixed in a temperature range of 20°C-30°C and then heated to at least about 70°C to form a polyurethane.

10        6. The process of claim 4 wherein the polymeric glycol is poly(tetramethyleneether-co-3-methyltetramethyleneether) glycol having a number average molecular weight of 2400-4500 and a 3-methyltetramethyleneether moiety content of 4-20 mole percent, and  
15        the addition ratio is 2.5-3.7.

7. The process of claim 1 comprising the additional step of heat-treating the spandex.

20        8. Spandex prepared by process of claim 1 of 5-2500 decitex.

9. The spandex of claim 9 of 10-135 decitex.

# INTERNATIONAL SEARCH REPORT

In tional Application No

PCT/US 98/18428

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08G18/28 D01F6/70

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08G D01F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 94 23100 A (DU PONT) 13 October 1994 see claim 1; example 3	1
A	----- CHEMICAL ABSTRACTS, vol. 124, no. 12, 18 March 1996 Columbus, Ohio, US; abstract no. 148609, XP002083849 see abstract & JP 07 305226 A (KURARAY CO.) 21 November 1995 ----- -/-	1

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

16 November 1998

Date of mailing of the international search report

01/12/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Hoffmann, K

# INTERNATIONAL SEARCH REPORT

Int lional Application No

PCT/US 98/18428

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CHEMICAL ABSTRACTS, vol. 124, no. 8, 19 February 1996 Columbus, Ohio, US; abstract no. 90160, XP002083872 see abstract & JP 07 278246 A (TOYO BOSEKI) 24 October 1995 ----	1-9
A	US 3 649 600 A (HARPER CYRIL N ET AL) 14 March 1972 cited in the application see claim 1 -----	1-9

# INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. l. Application No

PCT/US 98/18428

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9423100 A	13-10-1994	US 5362432 A BR 9405849 A DE 69401749 D DE 69401749 T EP 0692039 A JP 8508552 T	08-11-1994 26-12-1995 27-03-1997 04-09-1997 17-01-1996 10-09-1996
US 3649600 A	14-03-1972	BE 675661 A CH 465759 A DE 1669550 A FR 1466042 A GB 1064229 A NL 6600989 A SE 318723 B	16-05-1966 13-05-1971 31-03-1967 28-07-1966 15-12-1969

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**